


- 1. Material** Substrate GaAlAs (P Type) Removed
Epitaxial Layer GaAlAs (N/P Type)
- 2. Electrode** N(Cathode) Side Gold Alloy
P(Anode) Side Gold Alloy

3. Electro-Optical Characteristics

Parameter	Symbol	Min	Typ	Max	Unit	Condition
Forward Voltage	$V_{F(1)}$		1.1		V	IF=10uA
	$V_{F(2)}$			1.7	V	IF=50mA
Reverse Voltage	V_R	5			V	IR=10uA
Power	P_O	20	24		mW	IF=50mA
Wavelength	λ_P		878		nm	IF=50mA
	$\Delta\lambda$		45		nm	IF=50mA
Rise Time	T_r		28		ns	
Fall Time	T_f		18		ns	

※ Note : Power is measured by Sorter E/T system with bare chip.

- 4. Mechanical Data**
- | | |
|---------------------|-------------------------|
| (a) Emission Area | ----- 14.7mil x 14.7mil |
| (b) Bottom Area | ----- 15.7mil x 15.7mil |
| (c) Bonding Pad | ----- 150um |
| (d) Chip Thickness | ----- 8mil |
| (e) Junction Height | ----- 3.5mil |



AUK Corp.

Eoyang factory, 513-5 Eoyang-dong, Iksan, 570-210, Korea

Tel. +82 63 839 1111 Fax. +82 63 835 8259

www.auk.co.kr

